

To achieve high current carrying capabilities in YBCO coated conductors based on cube textured metal substrates, the texture and stability of the buffer/metal interface is a necessary requirement. In this work cube textured Ni-4at.%W substrate tapes were subjected to different H₂S treatments and the texture development of post-deposited MgO buffer layers was studied. The in-plane orientation and the texture sharpness of the MgO layers was found to depend strongly on the heat treatment time in Ar-10 ppm H₂S. Increasing the time from 5 to 60 min at 800°C changes the in-plane orientation from 45° over 0° to 45° at 15 min and the texture sharpens continuously to an FWHM (220) of < 6°.

TT 7.14 Mon 14:00 P1

Physical properties of chemically deposited La₂Zr₂O₇ and CeO₂ buffer layers on cube textured Ni-4 at.% W substrates — ●GUNTER KOTZYBA, BERNHARD OBST, RAINER NAST, and WILFRIED GOLDACKER — Forschungszentrum Karlsruhe, Institut für Technische Physik, P.O. Box 3640, 76021 Karlsruhe

The chemical solution deposition route for YBCO-coated conductors is of interest as a promising way to develop a low cost conductor. Thin films of La₂Zr₂O₇ and CeO₂ were prepared on Ni-4 at.% W by dip coating. The layers serve as buffer for depositing superconducting YBCO on top of it. We systematically investigated the dependence of the thickness on the viscosity and the concentration of the La (III) and Ce (IV) precursor solutions by means of a cone plate rheometer and an ICP OES. The roughness was analysed with a profilometer, the thickness determination was done by X-ray microanalysis. EBSD mappings show very good cube in-plane and out-of-plane texture.

TT 7.15 Mon 14:00 P1

dc and rf transport in normal and superconducting HTS, MgB₂, and Nb networks — ●JÜRGEN HALBRITTER — Forschungszentrum Karlsruhe, Postfach 36 40

Island/grain boundaries occur naturally in film growth or sintering. The hindrance of electric transport by boundary resistances $R_{bn}(Wcm^2)$ in distances $a_J(\leq 10mm)$ is easy to measure in normal conducting transport in such granular networks. The resistivity $r(T) = R_{bn}/a_J + p(\rho^i(T) + \rho^i(0))$ is fitted to observations with percolation factors $p > 1$ by current diverting $a_J\rho^i(300K)$ boundaries with $R_{bn} \geq a_J\rho^i(300K)$ where $\rho^i(T) + \rho^i(0)$ is due to the grain interior (IG) and R_{bn}/a_J and p describes the effects of boundaries (GB) and the network. In the superconducting transport GB may act as Josephson junctions (JJ) with $j_{cJ}(A/cm^2)$ as current density. For superconducting networks is a simple separation in IG and GB not possible. But low I_c values, $p > 1$ and large R_{bn} values are clear indications for growth boundary limitations. Analysis of $I_c(T, B, q, \omega)$ as junction of temperature, field B, angle q and frequency ω give crucial information about GB and flux low or pinning of Josephson (JF) or Abrikosov fluxons (AF) in the network. The combination of normal and superconducting analysis is of crucial importance for dc, ac and rf engineering applications and for the understanding of the related material science.

TT 7.16 Mon 14:00 P1

Electronic structure calculations for YBCO/metal interfaces — ●UDO SCHWINGENSCHLÖGL and COSIMA SCHUSTER — Institut für Physik, Universität Augsburg, 86135 Augsburg

Transport properties of heterostructures consisting of a metal and a correlated superconductor are of great importance for electronic devices based on HTSC. Using electronic structure calculations within density functional theory and the local density approximation, we investigate YBCO/metal interfaces. As the lattice mismatch between YBCO and Pd is rather small (0.7%), we choose Pd as the metallic constituent. It is generally accepted that the carrier density is modified at grain boundaries. Since this band bending should take place on the length scale of the lattice constant it can be reproduced by LDA supercell calculations. In particular, we use a supercell consisting of two YBCO unit cells alternating with five Pd layers along the orthorhombic c-axis. Following experimental results, the YBCO layers entering our calculations terminate by CuO chains.

Our results show that the electronic density of states at the interface depends crucially on the details of the local atomic structure. Therefore we have relaxed the atomic positions to minimize the forces on the ions. We compare two possible interface geometries, where the Pd atoms are placed on the Cu or O atoms of the CuO chains, respectively. For these configurations we determine the charge distribution across the interface.

TT 7.17 Mon 14:00 P1

Characterization of Top-Seeded Melt-Grown Bulk Superconductors by Hall Probe Mapping Techniques — ●S. HAINDL¹, H.W. WEBER¹, N. HARI BABU², D. A. CARDWELL², S. MESLIN³, J. NOUDEM³, L. SHLYK⁴, and G. KRABBES⁴ — ¹Atomic Institute of the Austrian Universities, TU Vienna, Austria — ²IRC in Superconductivity, University of Cambridge, UK — ³CRISMAT-ENSICAEN, CNRS/UMR, France — ⁴IFW Dresden, Germany

We report on the characterization of top-seeded melt-grown (TSMG) single grain bulk superconductors by two Hall probe mapping techniques. Scanning the trapped field distribution following magnetization of the sample in an external field is an established method of characterizing these materials. This technique enables both determination of the maximum trapped field after complete field penetration of the bulk sample, and identification of growth-induced inhomogeneities within the sample microstructure. A new mapping technique known as Magnetoscan has been developed over the past two years and recently improved to yield more useful information about the quality of bulk superconductors. This technique involves scanning simultaneously a small permanent magnet and a Hall probe over the unmagnetized superconducting surface of the bulk sample. Interesting results have been obtained using the magnetoscan technique, including direct imaging of different growth sectors in bulk samples and the identification of inhomogeneities such as cracks and grain-boundaries and the mapping of artificial holes in the single grain microstructure.

TT 7.18 Mon 14:00 P1

Nanometer-scale superconducting domains observed on NdBa₂Cu₃O_{7- δ} — ●PINTU DAS¹, DIRK MAUTES¹, MICHAEL R. KOBLISCHKA¹, THOMAS WOLF², and UWE HARTMANN¹ — ¹Institute of Experimental Physics, University of Saarbruecken, D-66041 Saarbruecken, Germany — ²Forschungszentrum Karlsruhe GmbH, Institute of Solid State Physics, D-76021 Karlsruhe, Germany

In understanding high temperature superconductivity, the recent focus is at the local-scale electronic modulation and its influence towards superconductivity in general. The granular structure and atomic-scale modulation of the density of states in Bi₂Sr₂CaCu₂O_{8+ δ} have been observed [1,2]. Here we report Scanning Tunneling Spectroscopic (STS) results obtained on the (ab) plane of a slightly underdoped NdBa₂Cu₃O_{7- δ} (T_c= 93.5 K) twinned single crystals at 4.2 K. Recent results proved that the NdBCO surface is highly clean and stable in air, showing atomic resolution at room temperature [3]. We used the STS imaging technique to study the electronic inhomogeneity and we observe that there are superconducting domains of ~ 3 nm length scale separated by nonsuperconducting regions, similar to that observed in Bi₂Sr₂CaCu₂O_{8+ δ} . In the superconducting domains, the size of the energy gap spatially varies from ~ 16 meV to ~ 44 meV. The average gap size is found to be ~ 22 meV. We discuss these data and the possible origin of the inhomogeneous electronic structure of the respective materials.

[1] Lang et al., Nature 415, 412 (2002)

[2] McElroy et al., Nature 422, 592 (2003)

[3] Ting et al., Appl. Phys. Lett. 72, 2035 (1998)

TT 7.19 Mon 14:00 P1

Nanoscale stripe structures in SmBa₂Cu₃O_x superconductors — ●M. WINTER¹, M. R. KOBLISCHKA¹, TH. WOLF², X. YAO³, A. HU⁴, and U. HARTMANN¹ — ¹Institute of Experimental Physics, University of Saarbrücken, P.O.Box 151150, 66041 Saarbrücken, Germany — ²Forschungszentrum Karlsruhe GmbH, Institute of Solid State Physics, D-76021, Karlsruhe, Germany — ³Department of Physics, Shanghai Jiao Tong University, 1954 Huashan Road, Shanghai 200030, P. R. China — ⁴Department of Physics, University of Waterloo, 200 Univ. Ave. West, Waterloo, ON N2L 3P7, Canada

AFM and STM scans on SmBa₂Cu₃O_x (SmBCO) melt-processed samples prepared using different techniques revealed the presence of nanoscale stripe-like structures, sometimes parallel over several micrometers, sometimes wavy. These structures consist of chemical compositional fluctuations and act as effective δT_c pinning centers due to their wavelength of typically 10-60 nm which is comparable to the ideal pinning-center size of 2ξ (≈ 10 nm for YBa₂Cu₃O_x in the ab-plane). Compared to similar structures in ternary (Sm,Eu,Gd)Ba₂Cu₃O_x (SEG) and (Nd,Eu,Gd)Ba₂Cu₃O_x (NEG) systems, where the stripes appear either as plateau-like stripes or as chains of aligned clusters, the stripes in SmBCO always appear as plateau-like stripes with a height of 1 Å-8 Å. These pinning structures throughout the whole sample volume may be a key

to improve critical current densities especially at high external magnetic fields.

TT 7.20 Mon 14:00 P1

How superstructure free is superstructure free Pb-BSCCO ? — ●L. DUDY, B. MÜLLER, B. ZIEGLER, A. KRAPP, H. DWELK, R.-P. BLUM, C. JANOWITZ, and R. MANZKE — Institut für Physik, Humboldt-Universität zu Berlin, Newtonstraße 15, 12489 Berlin

Pb- substituted BSCCO single crystals have been investigated by LEED and variable temperature VT- STM. While LEED pictures showed no superstructure spots in the range $30\text{eV} \leq E_{kin} \leq 320\text{eV}$, a closer look by VT- STM revealed that an ordered, alternating topographical formation of nano- domains with and without superstructure occurred. Independent of these geometrical nano- domains a long range ordering in the local density of states detected by corrugation analysis was also observed.

TT 7.21 Mon 14:00 P1

Unusual Nernst effect in various superconductors — ●C. HESS¹, E. AHMED¹, C. FALKENBERG¹, D. SOUPTTEL¹, G. BEHR¹, B. BÜCHNER¹, U. AMMERLAH², and A. REVCOLEVSCHI² — ¹IFW Dresden, Germany — ²Laboratoire de Physico-Chimie des Solides, Université Paris-Sud, France

We present experimental results of the Nernst-effect in the normal state of various superconductors. In particular, we investigated the high temperature superconductor $\text{La}_2\text{Sr}_x\text{CuO}_4$ with and without Eu-doping. The Eu-ions suppress superconductivity and stabilize a stripe phase in the CuO_2 -planes of the materials. We find that the relatively large Nernst-coefficient which has previously been reported for the normal state in pure $\text{La}_2\text{Sr}_x\text{CuO}_4$ is also present in the Eu-doped materials extending deep into the stripe ordered phase. We compare these results with the Nernst-effect of the superconductor $\text{YNi}_2\text{B}_2\text{C}$.

TT 7.22 Mon 14:00 P1

Rare earth substitutions and phase diagram studies in the ruthenocuprate system — ●EUGENIO CASINI¹, THOMAS P. PAGAGEORGIOU², ANTONIO VECCHIONE³, CONSIGLIA TEDESCO⁴, and HANS F. BRAUN¹ — ¹Physikalisches Institut, Universität Bayreuth, D-95440 Bayreuth, Germany — ²Hochfeld-Magnetlabor Dresden, Forschungszentrum Rossendorf, D-01314 Dresden, Germany — ³INFN and Dipartimento di Fisica "ER Caianiello", Università di Salerno — ⁴Dipartimento di Chimica, Università di Salerno, I-84081 Baronissi (Salerno), Italy

Coexistence of superconductivity and magnetism in the ruthenocuprate compounds has been the object of many investigations. $\text{RuSr}_2\text{GdCu}_2\text{O}_{8-\delta}$ is the most studied member of this class of materials and is the first and single known oxide in the quinary Sr-Gd-Ru-Cu-O system. Discording studies about the effect of the rare earth elements on the crystal structure and physical properties of these materials are reported. The formation of the $\text{RuSr}_2\text{NdCu}_2\text{O}_{8-\delta}$ compound is investigated following different preparation paths. Under standard conditions with the reported nominal composition a three-phase mixture is obtained. The concurring phases are identified as: $(\text{Sr}_{1-x}\text{Nd}_x)(\text{Ru}_{1-x}\text{Cu}_x)\text{O}_y$, $\text{Sr}_2\text{NdRuCuO}_7$ and $(\text{Sr}_{14-x}\text{Nd}_x)\text{Cu}_{24}\text{O}_{41}$. A characterization of these compounds is carried out by XRD, DTA and EDX analysis whereas superconducting and magnetic properties are determined with ac and dc susceptibility measurements. Magnetic transitions in the temperature range 10-20K and 20-30K are detected for the $\text{Sr}_2\text{NdRuCuO}_7$ and $(\text{Sr}_{14-x}\text{Nd}_x)\text{Cu}_{24}\text{O}_{41}$ compounds, respectively. The $\text{Sr}_2\text{NdRuCuO}_7$ compound has not been previously reported.

TT 7.23 Mon 14:00 P1

Theory of magnetic excitations in bilayer cuprates — ●HIROYUKI YAMASE and WALTER METZNER — Max-Planck-Institute for Solid State Research, Heisenbergstrasse 1, D-70569, Stuttgart, Germany

We calculate the dynamical magnetic susceptibility $\text{Im}\chi(\mathbf{q}, \omega)$ in the bilayer t - J model in slave-boson mean-field approximation. At low temperature, where the d -wave superconducting state is realized, a pronounced peak in $\text{Im}\chi(\mathbf{q}, \omega)$ appears at $\mathbf{q} = \mathbf{Q} = (\pi, \pi)$ and $\omega = \omega_{\mathbf{Q}}^{\text{res}}$. For $\omega < \omega_{\mathbf{Q}}^{\text{res}}$ strong spectral weight spreads around \mathbf{Q} , forming a diamond shaped pattern in \mathbf{q} -space. This spectral weight is due to a collective mode, known as "resonance mode" in the cuprates. The ω versus \mathbf{q} dispersion of the mode is bent downwards around \mathbf{Q} . For $\omega > \omega_{\mathbf{Q}}^{\text{res}}$, strong signals of $\text{Im}\chi(\mathbf{q}, \omega)$ tracing an upward dispersion are found. In the normal state, $\text{Im}\chi(\mathbf{q}, \omega)$ exhibits only a broad maximum at $\mathbf{q} = \mathbf{Q}$, that is incommensurate signals appear only in the d -wave pairing state. The above results

hold in both odd ($q_z = \pi$) and even ($q_z = 0$) channels. The most relevant experimentally observed features of magnetic excitations in bilayer cuprates are well captured by slave-boson mean-field theory.

TT 7.24 Mon 14:00 P1

Theory of the in-plane anisotropy of magnetic excitations in YBCO — ●HIROYUKI YAMASE and WALTER METZNER — Max-Planck-Institute for Solid State Research, Heisenbergstrasse 1, D-70569, Stuttgart, Germany

A pronounced xy -anisotropy was observed in recent neutron scattering experiments for magnetic excitations in untwinned YBCO.[1] The relatively small anisotropy of the bare band structure due to the orthorhombic crystal symmetry seems to be enhanced by correlation effects. A natural possibility is that the system is close to a Pomeranchuk instability associated with a d -wave Fermi surface deformation (d FSD).[2,3] We investigate this possibility in the bilayer t - J model within a self-consistent slave-boson mean-field theory. We show that the d FSD correlations drive a pronounced xy -anisotropy of magnetic excitations at low doping and at relatively high temperatures, providing a scenario for the observed xy -anisotropy also in $\text{YBCO}_{6.6}$ and $\text{YBCO}_{6.5}$, and in the pseudogap phase. [1] V. Hinkov *et al.*, Nature **430**, 650 (2004). [2] H. Yamase and H. Kohno, J. Phys. Soc. Jpn. **69**, 332 (2000); **69** 2151 (2000). [3] C. J. Halboth and W. Metzner, Phys. Rev. Lett. **85**, 5162 (2000).

TT 7.25 Mon 14:00 P1

Theory of ultrafast nonequilibrium dynamics in superconductors — ●JULIA UNTERHINNINGHOFEN¹, ANDREAS KNORR¹, and DIRK MANSKE² — ¹Institut für Theoretische Physik, Nichtlineare Optik und Quantenelektronik, Technische Universität Berlin, Hardenbergstr. 36, 10623 Berlin — ²Max-Planck-Institut für Festkörperforschung, Heisenbergstr. 1, 70596 Stuttgart

A theory of the dynamical ultrafast optical excitation of model superconductors is presented. We consider excitation of a nonequilibrium quasiparticle distribution via a femtosecond optical pulse and the subsequent scattering with optical phonons. The scattering processes lead to a recombination of the excited quasiparticles to equilibrated cooper pairs. Using the density matrix formalism, relaxation processes on a picosecond timescale and time-resolved pump-probe spectra are calculated.

TT 7.26 Mon 14:00 P1

Spin and Charge Josephson effects between non-uniform superconductors with coexisting helimagnetic order — ●ILYA EREMIN^{1,2}, FLAVIO S. NOGUEIRA³, and RENE-JEAN TARENTO⁴ — ¹Max-Planck Institut für Physik komplexer Systeme, Nöthnitzerstr 38, D-01187 Dresden, Germany — ²Institut für Mathematische/Theoretische Physik, Technische Universität Carolo-Wilhelmina zu Braunschweig, D-38106 Braunschweig, Germany — ³Institut für Theoretische Physik, Freie Universität Berlin, Arnimallee 14, D-14195 Berlin, Germany — ⁴Laboratoire de Physique des Solides, UMR 8502 - Université Paris-Sud, Bât. 510, F-91405 Orsay Cedex, France

We consider the spin and charge Josephson current between two non-uniform superconductors with helimagnetic order. We demonstrate that the presence of the helimagnetic phase generates a spin Josephson effect and leads to additional contributions to both single-particle and Josephson charge current. It is shown that for such systems the AC effect differs more radically from the DC effect than in the case of a BCS superconductor. The most interesting effect occurs in the presence of an external magnetic field and in absence of voltage, where we show that the charge Josephson current can be tuned to zero while the spin Josephson current is non-vanishing. This provides a well controlled mechanism to generate a spin supercurrent in absence of charge currents.

TT 7.27 Mon 14:00 P1

Enhancement of pairing due to the presence of resonant cavities — ●K. MORAWETZ^{1,2}, B. SCHMIDT¹, M. SCHREIBER¹, and P. LIPAVSKY³ — ¹Institute of Physics, Chemnitz University of Technology, 09107 Chemnitz, Germany — ²Max-Planck-Institute for the Physics of Complex Systems, Nöthnitzer Str. 38, 01187 Dresden, Germany — ³Faculty of Mathematics and Physics, Charles University, Ke Karlovu 5, 12116 Prague 2

A correlated fermion system is considered surrounding a finite cavity with virtual levels. The pairing properties are calculated and the influence of the cavity is demonstrated. To this end the Gell-Mann and Goldberger formula is generalized to many-body systems. We find a possible enhancement of pairing temperature if the Fermi momentum times